

Description

The 8341 *No Clean Flux Paste* is designed for lead free alloys, but it also works well with conventional leaded solders. This tacky flux uses a mix of rosin, thickener, and high-grade synthetically refined resin. The flux provides fast and widespread wetting during soldering and leaves non-conductive and non-tacky residues.

Applications & Usages

The 8341 flux is used for solder touch ups, repairs, or reworks of surface mount assemblies.

The 8341 is re-flowable in air or nitrogen. It can be used with profiles with peak maximum up to 270 °C and reflow times between 30 to 90 seconds.

Benefits and Features

- Excellent wettability
- Clear, non-conductive, and non-tacky residues
- Usable for both lead free and leaded alloys

ENVIRONMENT
RoHS Compliant

Usage Parameters

<i>Properties</i>	<i>Value</i>
Shelf Life	2 y

Temperature Ranges

<i>Properties</i>	<i>Value</i>
Storage Temperature Limits ^{a)}	18 to 27 °C [65 to 80 °F]

a) Store at around room temperature and protect from direct heat or sunlight.

Flux Paste Properties

<i>Physical Properties</i>	<i>Method</i>	<i>Value</i>
Flux Classification	J-STD-004	ROLO
Flux Type		Rosin
Flux Activity		Low
Halides %(wt)		<0.05%
Acid Value	IPC-TM-650 2.3.13	116 mg KOH/g of non-volatile
Copper Mirror	IPC-TM-650 2.3.32	No removal of copper film
Corrosion Test	IPC-TM-650 2.6.15	Non-corrosive
Silver Chromate	IPC-TM-650 2.3.33	Pass
Surface Insulation Resistance (SIR)		
SIR, J-STD-004	IPC-TM-650 2.6.3.3	$2.4 \times 10^{13} \Omega$
SIR, Bellcore (Telecordia)	Bellcore GR-78-CORE 13.1.3	$5.2 \times 10^{12} \Omega$
Electromigration	Bellcore GR-78-CORE 13.1.4	Pass
Cleaning requirements	—	None

Cleaning

The no-clean residue does not need to be removed for typical applications.

If removal is desired, a solvent system like the *MG 4140* or *MG 413B* can be used. For best results, warm the cleaning solution to about 40 °C [104 °F].

Health and Safety

Please see the 8341 Safety Data Sheet (SDS) for more details on transportation, storage, handling and other security guidelines.

Environmental Impact:




This product meets the European Directive 2011/65/EU Annex II (ROHS); recasting 2002/95/EC.

Health and Safety: Avoid breathing fumes. Wear protective eye protection/face protection. Wash hands thoroughly after use.

HMIS® RATING

HEALTH:	* 2
FLAMMABILITY:	1
PHYSICAL HAZARD:	0
PERSONAL PROTECTION:	

NFPA® 704 CODES



Approximate HMIS and NFPA Risk Ratings Legend:

0 (Low or none); 1 (Slight); 2 (Moderate); 3 (Serious); 4 (Severe)

Application Instructions

Apply flux by brushing, dipping, or direct dispensing via the syringe.

Packaging and Supporting Products

Cat. No.	Packaging	Net Volume	Net Weight	Packaging Weight
8341-10ML	Syringe	10 mL 0.34 fl oz	8 g 0.28 oz	TBD TBD

TBD = To be determined

Suitable Flux Cleaners

- *Heavy Duty Flux Remover:* Cat. No. 413B-1L, 413B-4L, 413B-20L, 413B-425G
- *Flux Remover for PC Boards:* Cat. No. 4140-P, 4140-400G, 4140-1L, 4140-4L, 4140-20L

Technical Support

Contact us regarding any questions, improvement suggestions, or problems with this product. Application notes, instructions, and FAQs are located at www.mgchemicals.com.

Email: support@mgchemicals.com

Phone: +(1) 800-340-0772 (Canada, Mexico & USA)

+ (1) 905-331-1396 (International)

Fax: + (1) 905-331-2862 or + (1) 800-340-0773

Mailing address: Manufacturing & Support
1210 Corporate Drive
Burlington, Ontario, Canada
L7L 5R6

Head Office
9347-193rd Street
Surrey, British Columbia, Canada
V4N 4E7

Warranty

M.G. Chemicals Ltd. warrants this product for 12 months from the date of purchase by the end user. *M.G. Chemicals Ltd.* makes no claims as to shelf life of this product for the warranty. The liability of *M.G. Chemicals Ltd.* whether based on its warranty, contracts, or otherwise shall in no case include incidental or consequential damage.

Disclaimer

This information is believed to be accurate. It is intended for professional end users having the skills to evaluate and use the data properly. *M.G. Chemicals Ltd.* does not guarantee the accuracy of the data and assumes no liability in connection with damages incurred while using it.