



S4066 - High Temp Fiberglass Reinforced Paper Tape

Description	This single sided tape consists of a bi-directional fiberglass reinforced smooth crepe paper carrier and a solvent based rubber adhesive.
Product properties	It has very good tensile strength, and good adhesion and shear resistance, also to rough and difficult surfaces. Very good resistance to humidity and temperature.
Applications	It is used for splicing of a variety of materials such as glass fiber, textile, vinyl floor coverings, thick kraft paper and abrasive papers, particularly at high temperatures. Can also be used for sealing of aluminium and steel sheet metal rolls.
Storage and ageing	1 year shelf life whilst stored in original packaging and ambient room temperature. Keep out of direct sunlight.
Applying tips	All substrates should be clean and contamination free, a solvent such as Isopropyl-Alcohol is recommended for cleaning purposes, and the tape should be applied with pressure.
Additional technical properties	90° peel adhesion to steel: 13.7 N/25 mm. Quick-Stick to Kraft paper: 1.6 N/25 mm.

TECHNICAL DATA

Carrier	Paper	
Adhesive	Rubber	
Colour	Natural	
Liner	None	
Thickness Total	0,315 mm	12,4 Mils
Tack (90°)	● ● ● ● ● ● ● ●	
Tensile strength length	468 N/25mm	107 Lbs/inch
Tensile strength width	411 N/25mm	93,9 Lbs/inch
Elongation length	4 %	
Elongation width	4 %	
Temperature performance (short time)	204 °C	399 °F
Application temperature	Minimum 15 °C	Minimum 59 °F

Disclaimer: Values shown in this document are averages only. For legal reasons, we emphasize that the information on this data is available "as is" and that Stokvis Tapes, an ITW company, gives no guarantees with respect to the accuracy and completeness nor with respect to interpretations made on the basis of this information.

See our applicable delivery conditions. Each user should conduct his own tests to determine the suitability of the product for his intended use and shall assume all risks and liability in connection therewith. Stokvis Tapes cannot be held liable for any damages resulting from the unsuitability of the product. Many factors beyond the control of Stokvis Tapes may affect the use and performance of the product in a particular application, including the conditions under which the product is used and the time and environmental conditions in which the product is expected to perform. Since these factors are uniquely within the user's knowledge and control, it is essential that the user evaluates the Stokvis Tapes product to determine whether it is fit for a particular purpose and suitable for the user's method of application.

The information is available to the user for viewing, copying and distributing, provided that Stokvis Tapes, an ITW company, is always quoted as the source. The information is intended solely for informational and non-commercial use.

Intellectual property: Stokvis Tapes, an ITW company, reserves all rights regarding this document and the information contained herein. Reproduction, use or disclosure to third parties without express permission is strictly forbidden.

Stokvis Tapes (UK) Ltd
 Unit 8, Tring Industrial Estate
 Icknield Way, Tring, Hertfordshire
 tel +44 (0)14 42 82 17 00
 fax +44 (0)14 42 82 17 22
 www.stokvistapes.co.uk
 info@stokvistapes.co.uk