

TECHSIL AP-135

This adhesion promoter is a solvent based blend of silanes.

Features:

- Single component.
- Enhances adhesion to steel, aluminium and glass
- Suitable for use with polyurethane and epoxy resins.

Typical Properties of Uncured Material

Test	Unit
Colour	Clear/ water white
Viscosity (mPas)	50
Drying time @ 23°C	5 minutes
Specific gravity @ 23°C	0.8

Note: The above technical information and data should be considered representative or typical and should not be used for specification purposes.

Direction for Use:

Paint onto substrates with a clean paint brush and leave to dry

Surface Preparation:

Surfaces should be grease free and clean. Shot blasting steel is recommended.

Storage and Shelf Life:

12 month when stored at 5 – 25°C

DISCLAIMER

This information relates only to the specific material designated and may not be valid for such material used in combination with any other materials or in any other process. Such information is, to the best of the company's knowledge and belief, accurate and reliable as of the date indicated. However, no warranty guarantee or representation is made to its accuracy, reliability or completeness. It is the user's responsibility to satisfy themselves as to the suitability of such information for their particular use.

Contact Details

Techsil Ltd
Unit 34, Bidavon Industrial Estate, Waterloo Road, Bidford on Avon, Warwickshire, B50 4JN
Tel: +44(0)1789 773232 Fax: +44(0)1789 774239 Email: sales@techsil.co.uk Web: www.techsil.co.uk